



CHEMICAL RESISTANCE

OF PLASTICS SPECIFIC TO THE 376 SERIES

Since many of LDPI's components are made of plastic materials, their resistance against chemical products may be limited or even nil. Consult this list before using aggressive detergents, disinfectants, or installing the luminaire in chemical hazardous areas (such as car washes, swimming pools, industrial kitchens, industrial laundries, slaughterhouses, livestock containment facilities, etc...) or in case of doubt, please contact us. For these conditions, appropriate products (like stainless steel latches, etc...) are available.

WARNING: The information in this chart has been supplied to LDPI, Inc. by other sources and is to be used ONLY as a guide in selecting light fixture for appropriate chemical compatibility. Before permanent installation, test the light fixture with the chemicals and under specific conditions of your application. Variations in chemical behavior handling due to factors such as temperature, pressure and concentrations can cause failure even though it passed an initial test.

- ① TASK
- ② PAINTBOOTH
- ③ VAPOR DUST
- ④ VAPOR
- ⑤ WET DAMP
- ⑥ MARINE
- ⑦ EXPLOSION PROOF
- ⑧ HID
- ⑨ INSPECTION
- ⑩ PORTABLE LIGHTING
- ⑪ MOUNTING
- ⑫ PHOTOMETRY
- ⑬ LAMPS BALLASTS
- ⑭ INFO
- ⑮ CUSTOM
- ⑯ ASK THE EXPERT

CHEMICAL	ACRYLIC	POLYCARBONATE	FIBERGLASS
ACIDS (Weak up to 10%)	+/-	+	+
ACIDS			
Acetic (max 30%)	-	+/-	+
Hydrochloric (max 20%)	+	+/-	+/-
Nitric (max 20%)	+/-	+/-	+/-
Sulphuric (max 50%)	+/-	+/-	-
Phosphoric	-	+/-	-
Hydrobomic	-	-	-
Accumulator Acid	+/-	+/-	+/-
BASES (Weak)			
Ammonia (max 25%)	+	-	+
BASES (Concentrated)			
Ammonia (max 50%)	+/-	-	+/-
Sodium Hydroide	+/-	-	-
SALT SOLUTIONS			
Common Salt	+	+/-	+
Metal Salt	+	+/-	+
Soda	+	+/-	+
HYDROCARBONS			
Aliphatic	+/-	+	+/-
Aromatic	-	-	+/-
Parafins	+	+	+
Carbon Dioxide, Carbon Monoxide	+	+	+
Ethyl Acetate	-	-	-
Pyridine	-	-	-
CHLORIDE HYDROCARBONS			
Carbon Tetrachloride	-	-	+/-
Trichlorethylene	-	-	-
Methylene Chloride	-	-	-
ALCOHOLS			
Up to 30%	+/-	+/-	+
Concentrated	-	-	+/-
Methanol, Ethanol, Phenol	-	-	+/-
ETHERS			
Ether	+/-	-	+/-
Petroleum Ether	+	+/-	+/-
AROMATIC HYDROCARBONS			
Aniline	+/-	-	+/-
Benzene and derivates	-	-	-
Hydrogen Peroxide	+/-	+/-	-
Xylene	-	-	-
OILS AND FATS			
Petrol, Kerosene	+/-	+/-	+
Mineral oil	-	+/-	+
Vegetable oils (hot)	+	-	+
Cooking fats (hot)	+	-	+
UNSATURATED CHLORIDE HYDROCARBONS			
Chloroform	-	-	-

+ = Resistant
 +/- = Limited resistant
 - = Not resistant

In case of limited resistance to corrosion (+/-) the use of polycarbonate clips is not suggested. We do advise the use of stainless steel latches if there is any uncertainty.